	<b>TYPICAL DATA SHEET*</b>	ISSUE DATE	Feb-15
	GRADE	<a href="http://WWW.ARTENPETRO.COM">WWW.ARTENPETRO.COM</a>	
	<b>GPPS 907</b>	Address: No 1331 ,alam al-hoda 1 St, Babaei , 2nd Phase,industrial Estat, Shokoochieh,Qom Iran Tell:+98(25)33346396 Fax:+98(25)33346473	

GPPS907 is a crystalline polystyrene with high heat resistance and molecular weight, used for extrusion and double

Oriented polystyrene (OPS) industry. Especially useful in the process of directly producing thick plates


Inject gas to make it have higher mechanical properties.

Applications: shower room, lighting film, heat insulation board, foam fruit tray, meat tray, egg box.

PROPERTY	UNIT	TEST METHOD	TYPICAL VALUE
<b>MELT FLOW INDEX(200°C-5KG)</b>	g/10min	<b>ASTM D-1238</b>	<b>8</b>
STYRENE RESIDUAL MONOMER	PPM	CLG LABPSG004 (ATOFINA TEST METHOD)	<500
<b>VICAT SOFTENING POINT ( 50 °C/hr 1kg)</b>	°C	ASTM D-1525	95
ROCKWELL HARDNESS	-	ASTM D-1525	L SCALE/ 70
TENSILE STRENGTH AT BREAK	MPA	ASTM D-638	43
ELONGATION AT BREAK	%	ASTM D-638	2
TENSILE MODULUS	MPA	ASTM D-638	3100

All the above data are typical values and cannot be used as actual data. Users should test and confirm the results by themselves.

The density and shrinkage of this grade are about 1.04 kg/liter and (0.4-0.7)% (ASTM D-955), respectively. If the quality of injection molded products is affected by moisture, GPPS particles can be dried at 70°C for 2-4 hours

	<b>STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*</b>	ISSUE DATE	Feb-15
	GRADE	<a href="http://WWW.ARTENPETRO.COM">WWW.ARTENPETRO.COM</a>	
	<b>GPPS 907</b>	Address: No 1331 ,alam al-hoda 1 St, Babaei , 2nd Phase,industrial Estat, Shokoochieh,Qom Iran Tell:+98(25)33346396 Fax:+98(25)33346473	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
<b>MELT FLOW INDEX (200 °C - 5KG)</b>	g/10min	ASTM D-1238	7-9
VICAT SOFTENING POINT ( 50 °C/hr 1kg)	°C	ASTM D-1525	MIN 93.5
RESIDUAL MONOMER	PPM	ATOCHEM PSG-004	MAX 500

FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT